

Raw Kaolin

Chemical Specification:-

Element	Result %
Silica (SiO ₂)	46 - 55
Alumina (Al ₂ O ₃)	33 - 35
Ferric Oxide (Fe ₂ O ₃)	0.20 - 2.00
Potassium Oxide (K ₂ O)	0.04 - 0.10
Sodium Oxide (Na ₂ O)	0.1 - 0.3
Loss on Ignition at 1,000o C	11.00 - 14.00

**ALEX INTERNATIONAL FOR
MINING AND REFRATORIES**



info@aimr-mining.com
www.aimr-mining.com